WTCI-569-P

PLAINTIFF'S EXHIBIT PX-709

THE PORT AUTHORITY OF NEW YORK AND NEW JERSEY

MEMORANDUM

To : Frank Boyce, Asbestos Project Coordinator, World Trade Center
From : Harry R. Pool, Jr.
Date : December 17, 1987
Subject: REQUEST FOR BULK SAMPLING - TWO WORLD TRADE CENTER 41ST FLOOR MECHANICAL EQUIPMENT ROOM
Copy to: N. Budeiri, R. Fagin, M.D., D. Montalbano, J. Panebianco, S. Samperi

As you requested, bulk samples of possible asbestos containing materials were collected and analyzed following the USEPA analytical procedure 600/M4-82-020. The following was disclosed:

Sample Number	Location	Result
2WTC-15615	Fluffy fallout insulation material taken from the floor near unit ACS-41-4	25% Chrysotile Asbestos
2WTC-15616	Fluffy fallout insulation material taken from the floor near unit ACS-14-4	Chrysotile Asbestos * (Trace)
2WTC-15617	Fluffy fallout insulation material taken from the floor near unit ACS-41-10	Non-Asbestos
2WTC-15618	Fluffy fallout insulation material taken from the floor near unit ACS-41-10	Non-Asbestos
2WTC-15619	Fluffy fallout insulation material taken from the floor of the upper part of M.E.R. by unit E-41-20	20% Chrysotile Asbestos
2WTC-15620	Cementitious fallout insulation material taken from the floor of the upper part of M.E.R. by unit E-41-20	<1% Chrysotile Asbestos

* Trace: A quality, much less than one percent, that is observable but too low a level to accurately quantify.

If you have any questions regarding these findings, please call me at PATHside (201) 963-7476.

Harry Pool

Harry R. Pool, Jr. Administrator
Inspection and Safety Programs
Inspection and Safety Division

AN/wgo